



HAL
open science

The nature of the deposited carbon at methane cracking over a nickel loaded wood-char

Chamseddine Guizani, Francisco Javier Escudero Sanz, Sylvain Salvador

► To cite this version:

Chamseddine Guizani, Francisco Javier Escudero Sanz, Sylvain Salvador. The nature of the deposited carbon at methane cracking over a nickel loaded wood-char. WasteEng 2014 - 5th International Conference on Engineering for Waste and Biomass Valorisation, Aug 2014, Rio de Janeiro, Brazil. p.1794-1808. hal-01709739

HAL Id: hal-01709739

<https://imt-mines-albi.hal.science/hal-01709739>

Submitted on 7 Nov 2018

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

The nature of the deposited carbon at methane cracking over a nickel loaded wood-char

C. GUIZANI*, F.J. ESCUDERO SANZ, S. SALVADOR
RAPSODEE, Mines-Albi, France.

*Corresponding author: guizani.c@gmail.com, 0033619572786


Keywords: Biomass char; nickel impregnation; methane cracking; catalyst.

Abstract

The catalytic properties of raw biomass chars and Ni-loaded biomass chars prepared at a high-heating-rate were assessed in the methane decomposition reaction. The raw chars exhibited a moderated catalytic activity in methane cracking while the Ni-loaded chars showed a catalytic activity 10 times higher than the raw chars. The deposited carbon was a highly ordered one as evidenced by XRD, Raman analysis and oxygen reactivity tests. The activation energy in the combustion reaction was estimated to be 300 kJ/mol. These results indicate that biomass char can be an effective low-cost and active support for metal impregnation to be used in catalytic cracking of hydrocarbons for hydrogen production

1. INTRODUCTION

Methane can be decomposed into carbon and hydrogen according to the moderately endothermic reaction:



Due to the strong C-H bonds, non-catalytic thermal cracking of methane requires temperatures higher than 1200°C to obtain a reasonable yield. Using a catalyst allow to reduce markedly the temperature. Common used catalyst are metal based and carbon based ones [1]. Ni and Fe based catalysts are widely used and exhibit very good activities in methane decomposition. The performance of a catalyst depends on the nature of the support. Common metal supports are alumina, SiO₂, metal oxides and zeolites[2].

Carbonaceous catalysts have been also tested in methane decomposition. These materials are less expensive, have a higher temperature resistance and are tolerant to sulfur and other harmful impurities that cause deactivation in metal based catalysts. A wide range of carbonaceous materials for catalysis application in methane decomposition was investigated in the literature [3] [4] [5]. The focus is mainly on activated carbons (manufactured from different carbon-based sources) and carbon blacks due to their good activities and stabilities over time.

For instance, Muradov et al. [3] investigated the catalytic activity of various carbon based materials such as activated carbon, carbon black, glassy carbon, acetylene black, graphite, diamond powder, CNT and fullerene. The authors found that there is a linear correlation between the initial methane decomposition rate and the specific surface area of the carbon material. This linear relation is only valid in the surface area range of 5 to 1200 m²/g. The authors stated that the catalytic activity of a carbon is rather related to its level of structural ordering. The less ordered are the carbons, the most efficient they are for methane decomposition. Activated carbons and carbon blacks (amorphous, micro-crystalline) being thus more efficient for methane catalytic decomposition than graphite, diamond and carbon nano-tubes (highly ordered carbons).

Commercial activated carbons (AC) can also be used as active supports for metal catalysts such as nickel which leads to a net increase in the catalytic activity of the material [6] [7]. For instance, Sarada et al. [7] studied the methane decomposition over Ni-loaded coconut shells activated carbon. AC samples were impregnated with an acetone solution containing Ni-nitrate. The authors showed that the performance of the

catalyst depends on the loading amount of Ni and its particle size. Decomposition tests were performed for 4 h and showed that the optimal loading of nickel that ensures the best stability and maximum accumulated carbon along cracking (7.92 g C/g Ni) was 23% of Ni in AC.

Biomass chars can also be used as catalysts in methane cracking [8] [9] [10]. However, the raw char does not exhibit a sustained activity and are rapidly deactivated by pore blocking due to carbon deposition [11]. Klinghoffer et al. [9] reported maximum deposited carbon amounts of 0.05 to 0.2 g/g of char, for pine char obtained after gasification with steam and CO₂ at different conversion levels, which is a quite low activity.

Biomass chars can be loaded with Nickel for an enhanced catalytic activity in methane cracking. This can be done on the char or before the pyrolysis reaction by impregnating the parent biomass. Nickel wet impregnation on woody materials leads to a very good dispersion of the metal in the wood and in the char after the pyrolysis reaction [12]. Impregnation of the parent biomass has the advantage of providing an intimate contact of the nickel with the biomass during the pyrolysis, which modifies the pyrolysis reaction mechanisms, reducing tars via cracking reactions and enhancing the production of light gases [13][14]. For instance, Blin et al. [14] reported an increase in H₂ production of around 260% for a nickel-impregnated wood compared to a pyrolysis test without catalyst. The resulting char containing highly dispersed nickel particles can be used in catalytic cracking of hydrocarbons.

To the best knowledge of the authors, nickel-loaded activated carbons or biomass chars used for methane cracking are commonly prepared by a dry mixing or a wet impregnation of the chars. We choose, in the present study, to impregnate the parent material so to maximize the light gas production during pyrolysis and to obtain a good dispersion of the metal in the final char as proposed by Blin et al. [12] [14].

This study focuses on the final Ni-containing chars. Besides the evaluation of the catalytic activity in methane cracking, we followed the nickel fate during the three reactions of pyrolysis, methane cracking and combustion. We also looked closely on the deposited carbon structural properties and reactivity.

2. MATERIALS AND METHODS

A. Parent wood sample impregnation

Biomass samples are beech wood-chips provided by SPPS company (France). Raw samples were initially sieved. Biomass particle having size in the range of 4 to 5 mm and thickness of about 1 mm were selected to perform the pyrolysis experiments. Proximate and ultimate analysis of the biomass samples are presented in table 1. The results are given on a dry basis. The moisture content of the wood-chips was estimated to be 10 % ±1 %. Ni-loaded wood-chips were prepared following a wet impregnation method [12]. A load of 20 g of wood-chips was impregnated with 200 mL of nickel nitrate aqueous solution (1 mol Ni/l) prepared with Ni (NO₃)₂ 6H₂O (Sigma Aldrich, 99% purity). At low pH values, H⁺ protons compete with Nickel for adsorption on the functional groups. For that reason the pH of the solution was contentiously adjusted in the range of 6.5 to 7 with an ammonia solution (1M). Wood impregnation was carried out for 3 days at room temperature (293 K) and under magnetic stirring. The impregnated wood chips were afterwards filtered, washed with 500 mL of deionized water and dried at 323 K for 24 h.

B. Nickel identification and quantification

The nickel content in the dried impregnated wood sample was determined by optical emission spectrometry inductively coupled plasma (ICP-OES). We developed an analytical procedure involving calcination, mineralization and ICP analysis.

C. High-heating rate char preparation

The HHR-chars were prepared in an horizontal tubular reactor facility (HTR) at 850°C under pure nitrogen. The biomass particles are introduced in the hot zone within 5 s, which allows performing high heating rate pyrolysis. The pyrolysis duration was fixed at 1 min. The char particles are afterwards cooled

down under nitrogen to room temperature. Details about the experimental apparatus and pyrolysis procedure can be found elsewhere [15].

D. Characterisation of the biomass chars

Several techniques were used to characterize the biomass chars before and after the methane cracking reaction.

1) Chemical composition

The char chemical composition in terms of C, H and N was determined with an elemental analyser. Nickel content was determined as described above. The oxygen content is determined by difference.

Chemical composition, char reactivities as well as structural properties were investigated using an elemental analyser, surface area measurement, X-ray diffraction, RAMAN spectroscopy and Scanning Electron Microscopy observation. These techniques are described briefly in the next paragraphs.

2) Structural and textural properties

The char structure was observed via Scanning Electron Microscopy (SEM) performed in a Philips XL30 ESEM apparatus (FEI Company). Char X-ray diffraction data were collected using a Phillips Panalytical X'pert Pro MPD diffractometer with a Cu K α (1.543 Å) radiation source. The BET surface area of the chars was determined with MICROMETRICS ASAP 2010 using nitrogen as gas adsorbate with the data collection from relative pressure (P/P^0) of 0.03 to 0.99. Raman spectra of the chars were recorded with a WITec Confocal Raman Microscope (WITec alpha300 R, Ulm, Germany). Raman spectroscopy allows a differentiation of the different carbon allotropes (pyrolytic carbons, graphitic carbons, carbon nanotubes (CNT), diamond etc...) in the char sample due to their different carbon bonds type and orientations.

3) Char reactivity : Temperature programmed oxidation

Temperature Programmed Oxidation (TPO) tests were performed on the initial chars as well as on those containing the deposited carbon after the cracking reaction. Experiments were performed in a STA 409 Netzsch thermogravimetry apparatus. A mass of initial char or char/deposited carbon (DC) composite of about 10 mg is heated to a final temperature of 550°C (for initial chars) or 750°C for (for char/DC composite) at 5°C/min in a 16% O₂ containing atmosphere. The final temperature was increased for the combustion of the char/DC sample as it contained a very stable carbon form. The TPO technique allows distinguishing different forms of carbon with respect to their thermal properties and reactivity towards oxygen. These combustion tests were done to check the feasibility of nickel recovery after the cracking reaction as well as to determine the kinetic parameters related to the oxidation reaction of the deposited carbon on the biomass char-Ni support.

E. Temperature programmed methane cracking reaction

The catalytic properties of the raw-char and Ni-char samples for methane cracking were tested in a TG device. Experiments were made in a STA 409 Netzsch thermogravimetry apparatus. A char sample of about 10 mg is used for the cracking reaction. After a complete reactor purge in a mixture of 5% of CH₄ in Argon, the char sample is heated -under the same atmosphere- from room temperature up to 900°C at 10°C/min and kept at this final temperature for 1 h. The total gas flow was 100 ml/min. The mass evolution of the char sample is recorded throughout the reaction.

3. RESULTS AND DISCUSSION

A. Nickel impregnation on the wood-chips

TABLE 1 shows the proximate and ultimate analysis of the raw and nickel-doped wood.

TABLE 1: PROXIMATE AND ULTIMATE ANALYSIS OF THE BEECH WOOD-CHIPS (DRY BASIS)

	Proximate analysis			Ultimate analysis				
	<i>VM</i>	<i>Ash</i>	<i>FC</i>	<i>C</i>	<i>H</i>	<i>O</i>	<i>N</i>	<i>Ni</i>
Raw-wood	88.1	0.4	11.5	46.1	5.5	47.9	0.1	0
Ni-wood	-	3.0	-	42.0	5.4	51.8	0.8	2.9

Nickel impregnation led to a decrease in the C and H contents and in an increase in the O and N contents. This can be explained by the ion exchange mechanism, loss of organic extractible, adsorption of nickel nitrate NiNO_3^+ and ammonium NH_4^+ cations which are source of nitrogen. The alkali content of the impregnated wood was very low (<0.1%) which can be explained by an exchange mechanism between nickel and AAEM species.

B. Char yields and characteristics

1) Chemical composition

The char yield, chemical composition and BET surface area of the two chars are given in TABLE 2. The char yield increased for the Ni-char due to the presence of nickel. The char yields are similar when considering an ash free basis. The carbon content of the Ni char is lower due to a dilution effect. The hydrogen content is also lower than in the raw-char. The nitrogen contents in the two chars are similar while the Ni-char contains more oxygen than the raw one.

TABLE 2. CHEMICAL COMPOSITION, YIELDS AND BET SURFACE AREA OF THE CHAR SAMPLES

	$Y_{\text{Char}} (\%)$	Ultimate analysis (% wt)					$S_{\text{BET}} (\text{m}^2/\text{g})$
		<i>C</i>	<i>H</i>	<i>O</i>	<i>N</i>	<i>Ash</i>	
Raw-char	11.7	87.91	1.97	6.16	0.96	3	69
Ni- -char	15.0	74.26	0.90	10	1.06	22	465

The nickel content in the Ni-char was determined by a gravimetric method. The residual mass after combustion tests in the TG device would correspond to the char ash content. Assuming a total recovery of the mineral matter after the pyrolysis step, the ash content (Ni + AAEM) would be 20%. The ash content in the Ni-char was found to be 22% that is slightly higher than the theoretical value. This can be due to a residual carbon remaining in the char or to sampling heterogeneity. But, regarding these results, we assume that the initial nickel remains entirely in the char after pyrolysis.

2) Structural features

A SEM observation shows a good dispersion of the nickel particles throughout the char. Nickel particles appear as bright spots on the SEM image. An example of the Ni-char surface image is given in *Figure 1*.




Figure 1. SEM image of the Ni-char

The size of the nickel particle is quite an important parameter in the methane cracking reaction [16]. The size distribution of the nickel particles shows that 90% of the nickel particles in the Ni-char have average sizes below 100 nm. The nickel particle size is known to be temperature dependent. Kodama et al. [17] impregnated a wood with a nickel solution and heated it to final temperatures of 500°C and 900°C. The authors observed that the metallic FCC Ni particles size increased from about 5 nm at 500°C to 20-200 nm 900°C. The size distribution found in the present work is similar to that of Kodama et al. at 900°C.

The BET surface area (Table 2) increased in the presence of nickel, from 69 m²/g in the raw char to 465 m²/g. The nickel is likely to catalyse the in-situ cracking of tars to light gases and hinder tar deposition on the pore mouths, which leads to an enhanced accessible surface area. It was also found in previous works to catalyse the graphitization of the char at temperatures as low as 500°C. The inside of the graphitic shells were empty which is synonym of an ordered structure with an accessible surface [17]. XRD patterns and Raman spectra are discussed in the next sections along with those of the char/DC.

3) Methane cracking reaction

Figure 2 shows the mass evolution of the two char samples during thermal decomposition of methane. It can be seen that for the raw char sample the mass initially decreased as a result of further heating and additional cracking. The mass decay was 6%. The nickel-loaded char showed very slight mass decay during heating. The nickel would have catalysed the tar cracking into light gas during the pyrolysis so that no further released is observed during additional heating.




Figure 2. Mass evolution of the char samples during thermal decomposition of methane

Methane decomposition reaction is assessed through the mass gain of the char sample corresponding to the amount of deposited carbon as a result of the methane decomposition into hydrogen and carbon following reaction (1). Since no other gaseous species except methane and argon are present in the reactor, it is therefore admitted that the mass gain corresponds to carbon deposition. Knowing the mass gain, we can determine the amount of deposited carbon, the amount of hydrogen produced and methane cracked by performing a straightforward mass balance.

TABLE 3. METHANE-CRACKING REACTION CHARACTERISTICS TABLE 3 summarizes the TG results related to the methane cracking reaction as to:

- the starting temperature of reaction: T_{start}
- the maximum reaction rate r_{max} (%/min)
- the temperature at the maximum reaction rate T_{rmax}
- the final amount of deposited carbon Y_{DC} (g/g of char)
- the final molar yield of H_2 : Y_{H_2} (mmol/g of char)

TABLE 3. METHANE-CRACKING REACTION CHARACTERISTICS

Char sample	T_{start} (°C)	r_{max} (%/min)	T_{rmax} (°C)	Y_{DC} (% of char)	Y_{H_2} (mmol/g of char)
Raw-Char	704	0.743	900	6.7	11.2
Ni -Char	704	3.0436	855	69.5	115.8

We can note that the raw char exhibits a moderate, but non negligible, catalytic activity for methane decomposition. The amounts of deposited is 6.7 g/100 g of char. Klinghoffer et al. [9] found similar amounts in the range of 5 to 20 g/100 g of char for chars gasified with CO_2 or H_2O in a pilot fluidized bed. Diffusion limitation and pore blocking are likely behind the rapid saturation of the char pores as reported by several authors [10] [11]. The carbon deposited has also a low catalytic activity for methane cracking, if not, the process would be continuous over the time [18][19].

Nickel loading greatly enhances the methane decomposition reaction as shown in in the TG curves. The amount of deposited carbon increased by 10 times for the Ni-char compared to the raw one. The amount of deposited carbon was 69.5 g/100 g of char. The starting temperature of the methane decomposition was 704°C for both chars. The temperature at the maximum reaction rate decreased by near to 50°C for the Ni loaded char.

4) On the nature of the deposited carbon

a) SEM observations

SEM images of the char/ DC after the cracking reaction are depicted in **Figure 3**. It can be seen that the carbon from methane grows on the char surface in the form of “filamentous” carbon and “carbon balls”. Both forms are growing on the nickel particles which are encapsulated inside. The deposited carbon forms a kind of shell around the nickel particles. Nickel particles can be observed either at the tip of the growing filaments or trapped along the hollow core of the nanofibers. These two forms have been reported in the literature [20] [21]. Suelves et al. [21] observed the formation of similar carbon fibers on a commercial catalyst containing 65wt% of Ni supported on a mixture of silica and alumina. The amount of deposited carbon was in the range of 0.5-9.3 g of deposited carbon/g of Ni, depending on the experimental conditions. In our case, the carbon yield is around 3 g of DC/g of Ni, nickel being considered as the active phase of the catalyst.




Figure 3. SEM images of the Ni-char surface after the cracking reaction

The mechanism of the formation of filamentous carbon has been thoroughly investigated from kinetics and thermodynamics considerations [22]. Similar carbon filaments formation has been observed over various catalysts such as Ni/ activated carbon [6], activated carbons from coal or coconut shell in which the carbon filaments formation has been attributed to iron and alkali species [23]. These observations indicate that the mechanisms of formation and growth of filamentous carbon on different supports are quite similar.

b) *X-ray diffraction*

XRD pattern of the raw char does not show a crystalline structure. However, crystalline structures have been observed for the Ni-char sample before and after the methane decomposition reaction. Results are shown on **Figure 4**. Before the cracking reaction, the Ni-char reveals the presence of crystalline Ni metal nano-phases with a face-centred cubic structure. This was expected regarding the results of Richardson et al. [12]. The XRD patterns of the Ni-loaded chars after the reaction are quite different from those of chars before the cracking reaction. Reflections at 44.5° , 51.7° , 76.3° and 98.4° corresponding to metallic nickel are still present, however other peaks appear. We can distinguish a very intense reflection at $2\theta = 26.1^\circ$ corresponding to a basal (0 0 2) inter-layer spacing ($d = 0.338$ nm) of a graphitic carbon. The peaks at 42.53° and 43.23° correspond respectively to the graphite (1 0 0) and (1 0 1). Reflection at 53.8° is attributed to graphite (0 0 4) while that at 77.6° is due to graphite (1 1 0). Reflections at 37.3° , 62.8° are quite ambiguous as they do not belong to metallic nickel nor to conventional graphite. Unless they belong to an unknown carbon crystal structure, they would most probably assigned to planes (1 1 1) and (2 2 0) of NiO, however we don't know by which mechanisms NiO is formed since it was not detected in the Ni-loaded char before the methane decomposition reaction.




Figure 4. XRD patterns of the Ni-char before and after the methane decomposition reaction (Ni-char +DC)

c) Raman spectroscopy

The deposited carbon is likely growing in the form of graphitic layers while the deposited carbon on the free-nickel chars was an amorphous one. No peaks related to an ordered structure were observed and the XRD patterns before and after the reaction were quite similar with no crystalline phase.

Figure 5 shows the Raman spectra of the free and nickel loaded chars before (Raw-char/Ni-char) and after the methane cracking reaction (Raw-char+DC/Ni-char+DC). These spectra show a common feature corresponding to 2 well-known bands related to carbon materials.




Figure 5. Raman spectra of the different samples.

The first band corresponds to the D-band (defect band) which appears typically in the wave number range of 1330-1360 cm⁻¹. This D-peak is related to a breathing mode of A_{1g} symmetry. This mode is forbidden in perfect graphite and only becomes active in the presence of disorder. This mode is also dispersive as it varies with the photon excitation energy. The intensity of the D-peak decreases with the extent of the presence of six fold rings corresponding to a more ordered structure [24]. The second band in the wave number range of 1570-1590 cm⁻¹ corresponds to the G-band (graphite band). The vibration G mode of graphite has an E_{2g} symmetry corresponding to an in-plane bond-stretching motion of pairs of C sp² atoms. The G mode does not require the presence of six fold rings, and therefore takes place at all sp² sites,

including those, which do not belong to a multi-ring systems. It is found for example in the spectra of aromatic molecules. For disordered carbon such as in biomass char, another signal corresponding to the amorphous carbon known as the A band, would appear as a broad peak at 1500 cm^{-1} [19]. A deconvolution process is therefore necessary to show the hidden peak. The more the char contains amorphous carbon, the more this A-band is intense, and the less the D and G peak are separated. Moreover, the deconvolution process allows having the accurate integral intensity of the D and G bands, which ratio, $I(D)/I(G)$, have been demonstrated to be well representative of the microstructure of a heterogeneous carbon material [19]. In the deconvolution process, we considered these 3 peaks and a curve fitting method including Lorentzian and Gaussian lines. The deconvoluted signal is presented in **Figure 6.a** and **b** for the raw-char and Ni-char and in **Figure 6.c** and **d** for raw-char+DC and Ni-char+DC. We can see that the Raman signal is quite well represented by these three main peaks. We can see for the raw char that the signal corresponding to the amorphous carbon (A-band) slightly decreased after the cracking reaction in comparison with the G and D bands that become sharper and more separated. This is due to the ordered carbon deposition and continuous heating of the sample that reduces the amorphicity degree.




Figure 6. Raman signal deconvolution for the char sample before and after the cracking reaction. a:raw-char, b:Ni-char, c:raw-char+DC, d:Ni-char+DC

The A-band signal is much lower relatively the D and G peaks in the Ni-char. This again confirms the role of the nickel in catalysing the graphitization of the char. The A-band signal completely disappeared after the methane cracking reaction. Even if an amorphous carbon is still present, its signal would be quite lower than those of the inherent graphitized carbon and the well ordered deposited one. The different peak positions as well as the ordering index IG/ID are given in **TABLE 4**.

TABLE 4. MAIN PEAK POSITION AND IG/ID RATIO FOR THE DIFFERENT CARBONEOUS SAMPLES

Char	Peak position			IG/ID
	D peak	A peak	G peak	
R-char	1349	1520	1592	0.99
Ni-char	1344	1536	1590	0.97
R-char+DC	1339	1509	1592	0.99
Ni-char+DC	1344	-	1572	1.42

For the Ni-char, after the cracking reaction, another peak appears at 2674 cm^{-1} . This one is characteristic of graphite material which consists of stacks of sp^2 bonded planar graphene sheets. Its intensity is less than the intensity of the G-band. The reverse case is observed for single graphene layers. The deposited carbon from methane likely forms a graphitic structure on the nickel loaded char. Another worth-noting fact is that a small peak appears at the very beginning of the spectra at 118 cm^{-1} . This peak is specific to the Radial Breathing Mode or RBM bands. The RBM bands are unique to Single Walled Carbon Nano Tubes (SWCNTs) and as their name suggests, correspond to the expansion and contraction of the carbon nano tubes (CNT). Altogether, these data indicates that the deposited carbon is well ordered and it is mainly in the form of graphite. It can also forms CNT on the small Ni particles which are scarce in the present case.

d) *Reactivity to oxygen: Temperature programmed oxidation*

The reactivity to oxygen of the Ni-char was investigated before and after the cracking reaction. The TG data are given in **Figure 7**. The heterogeneous carbonaceous material (Ni-char + DC) is clearly far less reactive to oxygen than the initial biomass char. The oxidation reaction started at 510°C for the Ni-char+DC composite while it started at about 320°C for the Ni-char. The well ordered deposited carbon is likely behind this thermal stability. The oxidation peak temperatures were respectively 400°C and 630°C for the initial chars and the Ni-char/DC composite. Similar oxidation parameters were reported by Pham-Huu et al. for the combustion of an Ni-loaded graphite/carbon nano fibers composite [25]. The Ni content of the composite is 11.83%. The theoretical value assuming that the nickel remains in the char during the cracking reaction would be 12.9%, which is quite similar. Here again, considering that the sampling before the combustion reaction does not allow to have the exact composition of the composite sample obtained after the methane decomposition, we can attribute this discrepancy to the sampling precision and consider that the nickel is recovered entirely after the combustion reaction.




Figure 7. Combustion TG curve of the Ni-char and Ni-char+DC

- *Kinetic parameters of the deposited carbon combustion reaction:*

The thermal stability of a carbonaceous material can be assessed through evaluating its reactivity to oxygen in a defined range of temperature. The thermal stability is also an index of the carbon ordering. The more the carbon oxidation reaction starting temperature is high, the more the carbon is ordered [25] [26].

Figure 8.a shows the DTG curve of the initial Ni-char. The DTG curve of the Ni-char oxidation shows one main peak with a small shouldering in the beginning. It has been reported that the presence of nickel catalyses the hydro-carbons (HC) cracking as well as the carbon graphitization during the pyrolysis step [12]. We assumed that the shouldering corresponds to the oxidation of a carbon (C_1) formed on the nickel particle

during the pyrolysis as a result of the HC cracking catalysed by the nickel particles. The main carbon is that relative to the biomass char C_{char} . The total carbon mass is given by the following equation:

$$\frac{C_{C1} + C_{char}}{m_{tot}} \times 100 = 100 - m_{Ni} \quad (2)$$

So that the total carbon mass is 78% following the experimental results. We considered two parallel combustion reactions corresponding to the reactions of carbon C_1 and C_{char} respectively with oxygen.

The combustion reactions are considered to be a first order reactions with respect to oxygen as well as to C_1 and C_{char} [27], the model then reads:

$$\frac{dm_{Ni-char}}{dt} = k_1 m_{C1} P_{O_2} + k_2 m_{Cchar} P_{O_2} \quad (3)$$

k_i is the rate constant which follows an Arrhenius law so that:

$$k_i(T) = A_i \exp \frac{-E_i}{RT} \quad (4)$$

Where A_i is the frequency factor [s^{-1}], E_i is the activation energy for the carbon “i” [J/mol], R and T are respectively the ideal gas constant [J/mol.K] and the temperature [K].

The best fitting parameters are given in TABLE 5. It can be seen on Figure 8 that with these parameters, the model fits well to the experimental results. The C_{char} mass is found to be 73 g while the C_1 carbon mass is found to be 3 g. The sum is quite close to the theoretical carbon amount of 78 g. The activation energy of C_{char} is found to be 139 kJ/mol which is the range of the activation energies given in Di Blasi’s review for the combustion of biomass chars [28]. That of the C_1 carbon is around 200 kJ/mol corresponding to a more ordered carbon form.

TABLE 5. MODELLING PARAMETERS FOR THE NI-CHAR COMBUSTION REACTION

Ni-char	$m_{C1} (g)$	$A_{C1} (s^{-1})$	$E_{C1} (kJ/mol)$
	3	3.10^{12}	203
	$m_{Cchar} (g)$	$A_{Cchar} (s^{-1})$	$E_{Cchar} (kJ/mol)$
	73	95000	139

Concerning the Ni-char/DC sample, we assumed that it contains two defined carbon types, namely C_{char} for the biomass char and C_{dep} for the deposited carbon. We neglected C_1 because of its low contribution in the mass of the final product Ni-char/DC.

The combustion reaction of the composite sample is considered to be the result of two parallel combustion reactions of C_{char} and C_{dep} . The combustion reactions are considered to be first order reactions with respect to oxygen as well as to C_{char} and C_{dep} .

According to the experimental data, in 100 g of the composite sample there would be $m_{Ni}=12$ g, $m_{Cchar}=46$ g, $m_{Cdep}=42$ g. Moreover, the activation energy of C_{char} is already defined by the first combustion experiment.

The mathematical transcription of these assumptions gives:

$$\frac{dm_{Ni-char+DC}}{dt} = k_3 m_{Cchar} P_{O_2} + k_4 m_{Cdep} P_{O_2} \quad (5)$$




Figure 8. Ni-char and Ni-char+DC reactivity modelling

One can see on **Figure 8** that the modeling results are quite satisfactory. The kinetic parameters determined for the best fit are given in **TABLE 6**. The mass of the two carbon forms are quite close to those given by the experiment. The activation energy of the DC oxidation is twice as high as that of the C_{char} carbon. This quite high activation energy reflects the oxidative stability of the DC.

TABLE 6. MODELLING PARAMETERS FOR THE NI-CHAR/DC COMBUSTION REACTION

Ni-char+DC	m_{Cchar} (g)	A_{Cchar} (s^{-1})	E_{Cchar} (kJ/mol)
		47	120
	m_{Cdep} (g)	A_{Cdep} (s^{-1})	E_{Cdep} (kJ/mol)
	43	$35 \cdot 10^{10}$	301

4. CONCLUSION

The nickel wood char exhibits a good catalytic activity in methane cracking compared to a free nickel wood char. Nickel being the active catalyst, the H_2 production was estimated to be 527 mmol/g of nickel. The deposited carbon forms a shell around the nickel particles. The whole is in the form of balls or filaments. The deposited carbon is highly graphitized as evidenced by XRD and Raman analysis. The end product is much more stable thermally due to the ordered nature of the deposited carbon. The activation energy in the combustion reaction of this latter was estimated to be around 300kJ/mol, twice as that of the conventional biomass char. This study is an exploratory one in using biomass char as nickel support for the methane cracking reaction. Further investigations are needed to optimize the reaction yield.

Acknowledgment

The author would gratefully thank Mr. Bernard Auduc for his technical support as well as Lauraine Haury for her help in the Raman spectroscopy analysis.

REFERENCES

- [1] H. F. Abbas and W. M. a. Wan Daud, "Hydrogen production by methane decomposition: A review," *International Journal of Hydrogen Energy*, vol. 35, no. 3, pp. 1160–1190, Feb. 2010.
- [2] Y. Li, D. Li, and G. Wang, "Methane decomposition to CO_x-free hydrogen and nano-carbon material on group 8–10 base metal catalysts: A review," *Catalysis Today*, vol. 162, no. 1, pp. 1–48, Mar. 2011.
- [3] N. Muradov, "Catalysis of methane decomposition over elemental carbon," *Catalysis Communications*, vol. 2, no. 3–4, pp. 89–94, Jul. 2001.
- [4] D. P. Serrano, J. a. Botas, J. L. G. Fierro, R. Guil-López, P. Pizarro, and G. Gómez, "Hydrogen production by methane decomposition: Origin of the catalytic activity of carbon materials," *Fuel*, vol. 89, no. 6, pp. 1241–1248, Jun. 2010.
- [5] S. Krzyzynski and M. Kozlowski, "Activated carbons as catalysts for hydrogen production via methane decomposition," *International Journal of Hydrogen Energy*, vol. 33, no. 21, pp. 6172–6177, Nov. 2008.
- [6] Z. Bai, H. Chen, B. Li, and W. Li, "Methane decomposition over Ni loaded activated carbon for hydrogen production and the formation of filamentous carbon," *International Journal of Hydrogen Energy*, vol. 32, no. 1, pp. 32–37, Jan. 2007.
- [7] J. Sarada Prasad, V. Dhand, V. Himabindu, and Y. Anjaneyulu, "Production of hydrogen and carbon nanofibers through the decomposition of methane over activated carbon supported Ni catalysts," *International Journal of Hydrogen Energy*, vol. 36, no. 18, pp. 11702–11711, Sep. 2011.
- [8] N. Muradov, B. Fidalgo, A. C. Gujar, N. Garceau, and A. T-Raissi, "Production and characterization of Lemna minor bio-char and its catalytic application for biogas reforming," *Biomass and Bioenergy*, vol. 42, pp. 123–131, Jul. 2012.
- [9] N. B. Klinghoffer, M. J. Castaldi, and A. Nzihou, "Catalyst Properties and Catalytic Performance of Char from Biomass Gasification," *Industrial & Engineering Chemistry Research*, vol. 51, no. 40, pp. 13113–13122, Oct. 2012.
- [10] a. Dufour, a. Celzard, V. Fierro, E. Martin, F. Broust, and a. Zoulalian, "Catalytic decomposition of methane over a wood char concurrently activated by a pyrolysis gas," *Applied Catalysis A: General*, vol. 346, no. 1–2, pp. 164–173, Aug. 2008.
- [11] a. Dufour, a. Celzard, B. Quartassi, F. Broust, V. Fierro, and a. Zoulalian, "Effect of micropores diffusion on kinetics of CH₄ decomposition over a wood-derived carbon catalyst," *Applied Catalysis A: General*, vol. 360, no. 2, pp. 120–125, Jun. 2009.

- [12] Y. Richardson, J. Blin, G. Volle, J. Motuzas, and A. Julbe, "In situ generation of Ni metal nanoparticles as catalyst for H₂-rich syngas production from biomass gasification," *Applied Catalysis A: General*, vol. 382, no. 2, pp. 220–230, Jul. 2010.
- [13] S. Hurley, H. Li, and C. C. Xu, "Effects of impregnated metal ions on air/CO₂-gasification of woody biomass.," *Bioresource technology*, vol. 101, no. 23, pp. 9301–7, Dec. 2010.
- [14] K. Bru, J. Blin, a. Julbe, and G. Volle, "Pyrolysis of metal impregnated biomass: An innovative catalytic way to produce gas fuel," *Journal of Analytical and Applied Pyrolysis*, vol. 78, no. 2, pp. 291–300, Mar. 2007.
- [15] C. Guizani, J. E. Sanz, and S. Salvador, "Effects of CO₂ on biomass fast pyrolysis: Reaction rate, gas yields and char reactive properties," *Fuel*, no. August, Aug. 2013.
- [16] D. Chen, K. Christensen, E. Ochoafernandez, Z. Yu, B. Totdal, N. Latorre, a Monzon, and a Holmen, "Synthesis of carbon nanofibers: effects of Ni crystal size during methane decomposition," *Journal of Catalysis*, vol. 229, no. 1, pp. 82–96, Jan. 2005.
- [17] Y. Kodama, K. Sato, K. Suzuki, Y. Saito, T. Suzuki, and T. J. Konno, "Electron microscope study of the formation of graphitic nanostructures in nickel-loaded wood char," *Carbon*, vol. 50, no. 10, pp. 3486–3496, Aug. 2012.
- [18] Y. Kameya and K. Hanamura, "Carbon black texture evolution during catalytic methane decomposition," *Carbon*, vol. 50, no. 10, pp. 3503–3512, Aug. 2012.
- [19] Y. Kameya and K. Hanamura, "Kinetic and Raman spectroscopic study on catalytic characteristics of carbon blacks in methane decomposition," *Chemical Engineering Journal*, vol. 173, no. 2, pp. 627–635, Sep. 2011.
- [20] J. Qiu, Y. Li, Y. Wang, C. Liang, T. Wang, and D. Wang, "A novel form of carbon micro-balls from coal," *Carbon*, vol. 41, no. 4, pp. 767–772, Jan. 2003.
- [21] I. Suelves, M. Lazaro, R. Moliner, B. Corbella, and J. Palacios, "Hydrogen production by thermo catalytic decomposition of methane on Ni-based catalysts: influence of operating conditions on catalyst deactivation and carbon characteristics," *International Journal of Hydrogen Energy*, vol. 30, no. 15, pp. 1555–1567, Dec. 2005.
- [22] A. M. Amin, E. Croiset, and W. Epling, "Review of methane catalytic cracking for hydrogen production," *International Journal of Hydrogen Energy*, vol. 36, no. 4, pp. 2904–2935, Feb. 2011.
- [23] K. K. Lee, G. Y. Han, K. J. Yoon, and B. K. Lee, "Thermocatalytic hydrogen production from the methane in a fluidized bed with activated carbon catalyst," *Catalysis Today*, vol. 93–95, pp. 81–86, Sep. 2004.
- [24] P. Larkin, *Interpretation, P. (n.d.). No Title*. 2011, p. 227.

- [25] C. Pham-Huu, R. Vieira, B. Louis, A. Carvalho, J. Amadou, T. Dintzer, and M. J. Ledoux, "About the octopus-like growth mechanism of carbon nanofibers over graphite supported nickel catalyst," *Journal of Catalysis*, vol. 240, no. 2, pp. 194–202, Jun. 2006.
- [26] L. Zhang, Z. Tan, S. Wang, and D. Wu, "Combustion calorimetric and thermogravimetric studies of graphite and coals doped with a coal-burning additive," *Thermochimica acta*, vol. 299, no. 97, pp. 13–17, 1997.
- [27] B. R. Stanmore, S. Salvador, and J. Commandre, "Reaction rates for the oxidation of highly sulphurised petroleum cokes : the influence of thermogravimetric conditions and some coke properties q," *Fuel*, vol. 82, pp. 715–720, 2003.
- [28] C. Di Blasi, "Combustion and gasification rates of lignocellulosic chars," *Progress in Energy and Combustion Science*, vol. 35, no. 2, pp. 121–140, Apr. 2009.

Appendix: Mass transfer modelling in the TG device

To check the accuracy of the thermogravimetric data, so that the reaction rate is effectively determined for a CH₄ concentration of 5% at the char bed surface, we considered a monodimensional diffusion model involving the diffusion of CH₄ from the top of the crucible where the concentration is $C_{CH_4}^\infty = 5\%$ to the char bed where the concentration is $C_{CH_4}^{S-bed}$ (zone 1), and a diffusion within the char bed with a volumetric reaction term (source term) corresponding to the methane consumption and hydrogen production (zone 2).




Fig. 1. Schematic representation of the TGA crucible

Fick’s second law in a steady state regime gives:

$$\text{div} (-D_{i-Ar} (\partial C_i / \partial z)) = R_i \quad (i = CH_4, H_2, Ar) \quad (3)$$

- D_{i-Ar} is the diffusional coefficient of specie “i” in argon [m^2/s]
- R_i is the source term [$kg/m^3.s$]

We considered in the present case the maximum reaction rate observed = 3%/min at $T = 900^\circ C$.

In the char bed (zone 2) an effective diffusion coefficient is calculated following the relation:


$$Deff_{i-Ar} = (\epsilon / \tau) D_{i-Ar} \quad (4)$$

- ϵ : porosity $\epsilon = 0.9$
- τ : tortuosity $\tau = 3$.

The effective diffusion coefficients in the char bed are corrected by the ratio ϵ / τ .

CH₄ consumption in the bed was calculated to be $0.134 \text{ kg}/m^3.s$ for a char bed dimensions of $l = 5 \text{ mm}$, $L = 5 \text{ mm}$ and $h_l = 1 \text{ mm}$.

The results of the model are shown in the figure below. The methane concentration at the bed surface is 4.5%. The thermogravimetric data are hence valid for our operating conditions.



Methane concentration profile for the maximum reaction rate at $900^\circ C$